

Valbruna Grade

SG5

Designations

Commercial name	Alloy 36
International Designation	Ni 36
W.N.	1.3912
UNS	K93601

Steel type

Electrical Resistance and Electronic Instrument Alloys

Specifications

DIN	17745
Other	SEW 385

Chemical composition

Chemical element	C	Mn	Si	Ni	Fe
Minimum value %	-	-	-	35%	balance
Maximum value %	0.1%	0.6%	0.5%	37%	balance

Head office and works:

Viale della Scienza, 25
 36100 VICENZA
 Tel. +39 0444 968211
 Fax. +39 0444 963836
www.valbruna-stainless-steel.com

Via Volta, 4
 39100 BOLZANO
 Tel. +39 0471 924111
 Fax. +39 0471 924497
www.valbruna-stainless-steel.com

2400 Taylor Street West
 46801 Fort Wayne, IN - USA
 Tel. +1 260 434 2800
 Fax. +1 260 434 2801
 E-mail: info@valbruna.us
www.valbrunastainless.com

Rev. 1/2020